

# DELO

## Instructions for Use & General Information on the Product Group

### **DELO®-CA**

Cyanoacrylates



### **Application areas**

DELO-CA are one-component adhesives on the basis of cyanoacrylic acid esters. They cure by contact with air humidity.

DELO-CA adhesives are preferably used for bonding plastics and elastomers (such as rubber) as well as for fast fixing of metals.

## **Preparation of the components to be bonded**

The contact surfaces must be free of oil, grease and other contaminations in order to achieve optimal bond strength. We provide our DELOTHEN cleaners. You can find more details in the “DELOTHEN Cleaners” technical information.

After cleaning, adhesion to the component can be further improved by surface pretreatment, which is described in the section “Curing”. You can find further information in the written information on surface pretreatment.

Before bonding, the components must be conditioned to room climate (temperature and air humidity).

The suitability and strength of the adhesive are to be verified on original components under application-specific conditions.

## **Processing**

The products are supplied ready for use. Depending on the scope of delivery, they can be processed manually directly from the container or by means of DELO dispensing units (e. g. pinch valve).

The adhesive is applied to only one component to be bonded. After adhesive application, the components are to be joined and possibly fixed speedily as curing of the adhesives is already triggered by the humidity available in the ambient air or condensing on the bonding surfaces.

Opened containers with DELO-CA must be used up within 4 weeks. It must be ensured that the adhesive stock remains closed so that no humidity can enter the containers.

Dispensing valves and product-guiding parts should be thoroughly cleaned before adhesive use. Residues of other products must be removed without leaving any residue. It is recommended that all product-guiding parts are made of non-polar plastics. As it is normally not or only hardly possible to clean product-guiding parts after using adhesives on the basis of cyanoacrylic acid esters, it is recommended to dispose of them after use. You can find more details in our technical information on equipment cleaners.

## **Curing**

DELO-CA adhesives cure at room temperature under the influence of air humidity. Normally, the humidity on the component surfaces is sufficient.

Ideal curing conditions are a relative humidity of 40 % to 80 % at approx. +23°C. If the relative humidity is lower, for example in winter in heated rooms, curing may be delayed or, in extreme cases, even be prevented.

For bonding plastics difficult to bond, that is to say non-polar types, the DELO-PRE 2005 primer can improve adhesion and is specifically recommended for DELO-CA adhesives. Apply the primer and, after complete evaporation, the adhesive.

If the normally very fast curing is delayed or disrupted by factors such as an oversized bonding gap, a porous surface or an open joint, the use of DELO-QUICK 2002 is possible.

Apply this activator to the porous or more inactive surface. After evaporation of DELO-QUICK 2002, the adhesive can usually be applied to the second component. In order to accelerate curing for open applications, the activator is sprayed directly onto the adhesive.

You can find the detailed, product-specific information on the processing of each product in the specific Technical Data Sheet.

## **Instructions and advice for occupational health and safety**

See Material Safety Data Sheet

## **Storage**

In unopened original container

Cool storage is recommendable.

Storage life: see Technical Data Sheet

# CONTACT

## **DELO** Industrial Adhesives

- ▶ **Germany** · Windach/Munich (Headquarters) · Phone +49 8193 9900-0 · [info@DELO.de](mailto:info@DELO.de) · [www.DELO.de](http://www.DELO.de)
- ▶ **China** · Shanghai · Phone +86 21 2898 6569 · [china@DELO-adhesives.com](mailto:china@DELO-adhesives.com) · [www.DELO-adhesives.com/cn](http://www.DELO-adhesives.com/cn)
- ▶ **Malaysia** · Kuala Lumpur · Phone +65 6807 0800 · [malaysia@DELO-adhesives.com](mailto:malaysia@DELO-adhesives.com) · [www.DELO-adhesives.com/en](http://www.DELO-adhesives.com/en)
- ▶ **Singapore** · Phone +65 6807 0800 · [singapore@DELO-adhesives.com](mailto:singapore@DELO-adhesives.com) · [www.DELO-adhesives.com/en](http://www.DELO-adhesives.com/en)
- ▶ **South Korea** · Seoul · Phone +82 31 450 3038 · [korea@DELO-adhesives.com](mailto:korea@DELO-adhesives.com) · [www.DELO-adhesives.com/en](http://www.DELO-adhesives.com/en)
- ▶ **Taiwan** · Taipei · Phone +886 2 6639 8248 · [taiwan@DELO-adhesives.com](mailto:taiwan@DELO-adhesives.com) · [www.DELO-adhesives.com/cn](http://www.DELO-adhesives.com/cn)
- ▶ **USA** · Sudbury, MA · Phone +1 978 254 5275 · [usa@DELO-adhesives.com](mailto:usa@DELO-adhesives.com) · [www.DELO-adhesives.com/us](http://www.DELO-adhesives.com/us)

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

© DELO – This document including any and all parts is protected by copyright. Any use not expressly permitted by the Urheberrechtsgesetz (German Copyright Act) shall require DELO's written consent. This shall apply without limitation to reproductions, duplications, disseminations, adaptations, translations and microfilms as well as to the recording, processing, duplication and/or dissemination by electronic means.

03/17