

# DELO

Instructions for Use &  
General Information  
on the Product Group

## DELO<sup>®</sup>-PUR

Two-component polyurethanes and  
silane-modified polyurethanes



## **Product details and application areas**

DELO-PUR products are two-component polyurethanes or silane-modified polyurethanes that usually cure at room temperature after mixing the two components. They are predominantly used as adhesives and casting compounds in electronics, electrical engineering, automotive, mechanical engineering, tool and aggregate construction.

Many DELO-PUR products are filled in DELO-AUTOMIX double chamber cartridges and can be easily mixed and dispensed by means of a dispensing gun and static mixing tubes. DELO supplies suitable mixing tubes we also use in internal development and testing.

## **Preparation of the components to be bonded**

The contact surfaces must be free of oil, grease and other contaminations in order to achieve optimal bond strength.

Condensation water on components must evaporate before adhesive application. Residues of the cleaning on the substrate are to be avoided.

Depending on the substrate, defined drying may be necessary for optimal results.

After cleaning, adhesion to the component can be further improved by surface pretreatment. You can find further information in the written information on surface pretreatment.

The suitability and strength of the adhesive are to be verified on original components under application-specific conditions.

## **Processing from hobbocks**

### **Preparation of the adhesive**

The products are usually ready for use. If the products are stored above or below room temperature, it must be ensured that the container is conditioned to room temperature before use. The containers are conditioned at room temperature (max. +25°C). Heat addition is not permissible. Condensation water on the substrate should be prevented.

### **Processing**

Two-component products consist of component A and B, which produce the ready-to-use adhesive only after careful and homogeneous mixing in the correct ratio. Therefore, the two-component products are offered as a set of both components with matched fill quantity and one single batch number. The data sheet and specification values are exclusively determined with components of the same batch and are only valid in this combination.

Opened containers with DELO-PUR must be used up within a maximum of 4 weeks (surroundings: +23°C, max. 50 % rel. humidity). It must be ensured that the stored adhesive is air- and humidity-tight (e.g. by the barrel follower plate on the supplied container) to prevent entering of air and humidity. Removal from the barrel press, reclosing and later reuse is not intended.

## Manual processing

Due to the exothermal curing reaction, large preparations should be mixed in several portions or flat vessels for a better heat dissipation.

Weigh out the components A and B in the mixing ratio indicated. Mix the mixture properly, that means free of streaks, in a suitable vessel. It must be ensured that no air is stirred into the adhesive and that all ingredients weighted out are mixed to a homogeneous preparation. Processing, i.e. mixing and dispensing must be completed within the processing time specified. Scrapers or notched trowels are suitable for application.

## Processing of polyurethanes from a hobbock

### Procedure

#### Component A:

1. Remove the cover
2. Remove cover foil and Styrofoam plate
3. Twist in projecting product foil and cut it off just above the fill level



4. Cut off the product foil at the edge of the hobbock



5. Then put the edge inwards



6. Insert the follower plate

**Component B:**

*This component is humidity-sensitive. Please make sure that no air humidity can penetrate the open container! This component also contains isocyanate.*

1. Remove the cover
2. Remove the desiccant
3. Open in-liner, see procedure for component A
4. Insert the follower plate

## **Processing of silane-modified polyurethanes from a hobbock**

### **Procedure**

**Component A:**

*This component is humidity-sensitive. Please make sure that no air humidity can penetrate the container!*

1. Remove the cover
2. Twist in projecting product foil and cut it off just above the fill level



3. Cut off the product foil at the edge of the hobbock



4. Then put the edge inwards



5. Insert the follower plate

#### **Component B:**

1. Remove the cover
2. Remove the protective sheet
3. Open in-liner, see procedure for component A
4. Insert the follower plate

### **System configuration**

During maintenance work, product exchange, etc. on dispensing systems, we recommend exchanging the media-carrying supply lines instead of cleaning or rinsing them. Please check the media-carrying parts, such as dispensing valves and product hoses, for compatibility with the adhesive or the components. Suitable materials predominantly include stainless steel and common plastics, such as PE, PP, PUR or PTFE. When choosing the material, the compatibility with polyols and isocyanates must be verified. We do not recommend using ignoble metals, copper and its alloys (e.g. Zn, Ni, Cu, Fe). When using cleaning agents, please note our indications for substances compatible with the specific adhesive. You can find more details in the technical information about cleaning agents.

## Processing from DELO-AUTOMIX cartridges



Video instructions for the setup of your device

[www.delo.de/login](http://www.delo.de/login)

User: **instduopoxpur** Password: **5F9QedT8**



The adhesives are applied by means of manual or pneumatic dispensing guns. Depending on adhesive, container and viscosity, a minimum dispensing pressure is required to completely empty the cartridge.

Direct pressurization of the cartridge is not recommended. Air may penetrate the adhesive past the piston. This can result in imprecise dispensing results and even air bubbles in the dispensed adhesive.

1. Insert double chamber cartridge in dispensing gun
  - Push the securing lever of the dispensing gun upwards
  - Insert the cograil from ahead to the end stop (cogging down)
  - Open the dispensing gun by flipping the cartridge retainer upwards
  - Insert double chamber cartridge
  - Close the cartridge retainer for cartridge arrangement
2. Equalize fill level deviations
  - Remove the end cap from the cartridge top by turning
  - Equalize fill level deviations by operating the trigger lever (disposal according to MSDS)
  - The double chamber cartridges are overfilled beyond the adhesive amount specified so that no loss occurs while equalizing the fill level deviations
3. Attach mixing tube
  - Attach the mixing tube and lock it by a quarter turn, or lock swivel nut by a quarter turn
4. Avoid mixing errors
  - Before use, abandon one content of the mixing tube in order to prevent mixing errors and ensure perfect adhesive curing (disposal according to Material Safety Data Sheet)
5. Adhesive application
  - Apply the homogeneously mixed adhesive to the component



After work finish or during breaks, the mixing tube can usually remain on the cartridge as closure instead of the original end cap.

If the processing pauses are shorter than the processing time of the 3 g preparation of the specific product, the same mixing tube can be used again.

Before processing continues after longer breaks, the previous mixing tube is removed, the outlet at the cartridge is ridded of possibly cured adhesive, and a new mixing tube is attached. When replacing the cartridge, we recommend that a new mixing tube is used in any case.

DELO-AUTOMIX cartridges are designed for being used in suitable dispensing guns (e.g. DELO-XPRESS series). The mixing tube should be mounted directly on the outlet of the cartridge. It is the user's responsibility to test the suitability of the selected dispensing equipment with the original product under close-to-production conditions.

## **Curing**

The adhesives usually cure at room temperature. After mixing the components, the period of time available for processing the product starts. During curing, exothermic reaction heat is generated. This depends on the adhesive and the adhesive quantity. After exceeding the processing time, the viscosity increases fast until complete curing resp. hardening. Temperatures below room temperature decelerate curing. In extreme cases, the product cures incompletely or not at all. Curing conditions deviating from room temperature can influence the product properties.

Complete curing of most products is achieved at room temperature in 7 days. The curing time of room-temperature-curing products can be reduced. For polyurethanes, this takes place from a temperature of +60 °C, and for silane-modified polyurethanes up to a maximum temperature of +60 °C.

You can find the detailed, product-specific information on the processing of each product in the specific Technical Data Sheet.

## **Instructions and advice for occupational health and safety**

Pay attention to the details provided in the Material Safety Data Sheet of the specific product and the hazard symbols on the labels of the adhesive containers.

## **Storage**

Storage life and storage temperature can be drawn from the Technical Data Sheet. The product may be stored in the unopened original container only.

# Label

Typical design of a GHS label at DELO. Depending on the container size, the design and content of the label may vary.



- 1 Product name
- 2 Container content (volume/weight)
- 3 Datamatrix  
Extended article number@Batch@Expiry date@Product name  
(1926618-Z01-EN@12345678@2021-01-30@DELO PRODUCT NAME)
- 4 GHS labeling
- 5 Article number
- 6 Batch number
- 7 Expiry date
- 8 Storage temperature

# CONTACT

**DELO Industrial Adhesives**  
Headquarters

▶ **Germany** · Windach / Munich .....

- ▶ **China** · Shanghai
- ▶ **Japan** · Yokohama
- ▶ **Malaysia** · Kuala Lumpur
- ▶ **Singapore**
- ▶ **South Korea** · Seoul
- ▶ **Taiwan, China** · Taipei
- ▶ **Thailand** · Bangkok
- ▶ **USA** · Sudbury, MA

..... [www.DELO-adhesives.com](http://www.DELO-adhesives.com)

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

© DELO – This document including any and all parts is protected by copyright. Any use not expressly permitted by the Urheberrechtsgesetz (German Copyright Act) shall require DELO's written consent. This shall apply without limitation to reproductions, duplications, disseminations, adaptations, translations and microfilms as well as to the recording, processing, duplication and/or dissemination by electronic means.