

DELO MONOPOX

Aminic epoxy resins

Application area	Constructional and structural adhesives							Low-temperature curing		Casting resins		Die attach		Anisotropic conductive adhesives (ACA)		
Product code	1197	AD066	AD286	AD295	HT281	HT282	SJ2720	LT204	LT2224	6093	6095	DA255	NU257	AC245	AC268	
Color <small>cured product</small>	silver gray	beige	silver gray	light beige	light gray	silver gray	beige	black	white fluorescent	black	black	gray	white	gray	black	
Filler	aluminum	unfilled	aluminum	minerals	minerals	aluminum	unfilled	minerals	minerals	unfilled	unfilled	unfilled	unfilled	nickel	nickel	
Density [g/cm ³] <small>at room temperature</small>	1.4	1.2	1.4	1.6	1.57	1.57	1.17	1.53	1.2	1.2	1.2	1.34	1.1	1.48	1.51	
Viscosity [mPas] <small>at +23°C</small>	pasty	20,000	110,000	230,000	125,000	125,000	14,000	20,000	20,000	31,000	50,000	25,000	29,000	33,000	32,000	
Curing time <small>Time/T [°C]</small>	<small>air convection oven</small>	40 min/+150 15 min/+180	20 min/+130	75 min/+130 40 min/+150 15 min/+180	40 min/+150	40 min/+150 also suitable for fast induction curing	20 min/+130	90 min/+60 15 min/+90	30 min/+60	30 min/+130	30 min/+130	8 min/+120 2 min/+150	20 min/+140	–	–	
	<small>thermode</small>	–	–	–	–	–	–	–	–	–	–	6 s/+180	8 s/+180	8 s/+180 6 s/+200	8 s/+170 6 s/+190	
Min. curing temperature [°C]	+130	+100	+130	+130	+130	+130	+100	+60	+60	+100	+100	+90	+100	+150	+150	
Temperature range of use [°C]	–55 to +200	–40 to +180	–55 to +200	–40 to +200	–55 to +220	–55 to +220	–40 to +180	–40 to +150	–40 to +150	–40 to +150	–40 to +130	–40 to +180	–40 to +150	–40 to +150	–40 to +150	
Temperature stability [MPa] <small>Al/Al sand-blasted</small>	<small>at +150°C</small>	5	–	6	9	12	12	–	–	–	–	–	–	–	–	
	<small>at +200°C</small>	–	–	3	3	4	4	–	–	–	–	–	–	–	–	
Die shear strength [MPa]	–	–	–	–	–	–	–	52 Al/PET	–	–	–	52.5 FR4	35 Al/PET	74 Al/PET	33 Al/PET	
Glass transition temperature T _g [°C]	+140 rheometer	+132 rheometer	+130 DMTA	+134 rheometer	+150 DMTA	+157 DMTA	+115 DMTA	+30 TMA	+25 DMTA	+93 rheometer	+87 rheometer	+139 DMTA	+145 DMTA	+149 DMTA	+138 DMTA	
Compression shear strength [MPa] <small>Al/Al</small>	–	60	52	–	55	49	41	27	12	–	–	48	36	–	–	
Tensile shear strength [MPa] <small>Al/Al sand-blasted</small>	26	18	33	30	24	29	13	20	11	14	18	–	–	–	–	
Tensile strength [MPa]	40	45	64	50	66	60	26	20	5	41	45	40	–	–	–	
Elongation at tear [%]	1.4	1.4	2.8	1.4	1.7	2	1	35	90	1.6	1.2	1.2	–	–	–	
Young's modulus [MPa]	3,300	2,900	3,800	5,500	5,700	4,800	2,900	400	100 DMTA	2,900	3,800	3,200	4,100 DMTA	3,900 DMTA	3,700 DMTA	
Shore hardness D	67	83	80	84	87	84	79	77	76 shore hardness A	74	83	86	87	85	83	
Coefficient of linear expansion [ppm/K]	<small>below T_g</small>	65	66	61	42	50	55	86	43	73	59	65	58	60	55	60
	<small>above T_g</small>	171	189	187	147	148	142	194	149	188	183	183	170	172	180	170
Shrinkage [vol. %]	3.0	2.0	2.5	2.5	2.0	2.7	2.1	4.0	3.8	1.1	2.0	1.7	1.4	1.6	1.3	
Water absorption [weight %] <small>24 h at room temperature</small>	0.1	0.2	0.18	0.12	0.10	0.10	0.15	0.2	0.6	0.1	0.1	0.2	0.03	0.1	0.25	
Dielectric strength [kV/mm]	2	–	5.2	20	22	–	–	–	–	18	–	–	–	–	–	
Storage life	<small>at rt (max. +25°C)</small>	6 weeks	4 weeks	4 weeks	4 weeks	4 weeks	4 weeks	2 weeks	72 h	24 h	6 weeks	6 weeks	72 h	1 week	1 week	72 h
	<small>0°C to +10°C</small>	6 months	6 months	6 months	6 months	6 months	6 months	4 months	–	–	6 months	6 months	–	–	–	–
	<small>–18°C</small>	–	–	–	–	–	–	–	6 months	4 months	–	–	6 months	6 months	6 months	6 months
Product features	high run resistance	for fast, high-strength bonds	very high strength excellent media resistance	good flow behavior excellent media resistance	excellent media and temperature resistance	excellent media and temperature resistance high strength on nickel impact-resistant	fast curing at moderate temperatures high-strength bonds	curing at very low temperatures good adhesion to LCP	curing at very low temperatures flexible	good flow behavior	excellent media resistance low chloride ion content	fast thermode curing possible excellent adhesion to FR4, gold, preplated leadframe, Al, and LCP	fast thermode curing possible	fast thermode curing possible excellent adhesion to PET, FR4, copper, Al, silver	fast thermode curing possible	
Typical application area	especially for metal bonding high-strength applications	especially for metal bonding good adhesion to many plastics excellent adhesion to PEEK	especially for metal bonding used in e-motors high-strength applications	especially for metal bonding high-strength applications	especially for metal bonding used in e-motors high-temperature applications	especially for metal bonding used in e-motors high-temperature applications	especially for metal bonding good adhesion to many plastics	camera bonding used for temperature-sensitive components	especially for electronic applications	bonding of bare semiconductors (ICs) to metal leadframes, rigid PCBs, and ceramic substrates	especially for electronic applications, smart labels, and smart cards	anisotropic electrical contacting of electronic components such as flip-chips				

AC = Anisotropic Conductive AD = Adhesive DA = Die Attach HT = High Temperature LT = Low Temperature NU = No Flow Underfiller SJ = Structural Joining

Product description

DELO MONOPOX are one-component, heat-curing epoxy resins.

Standard temperature range

The DELO MONOPOX epoxies are normally used in a temperature range of –55 °C to +220 °C.

Many product properties depend on the temperature and can change permanently, in particular at high temperatures. Therefore, it has to be checked before each use whether a certain adhesive is suitable for the temperatures in the required area of application. Please see the Technical Data Sheet for more information on how our products react to temperatures.

Processing

The products are normally delivered ready for use. They are applied directly from the container or using dispensing units.

Curing

DELO MONOPOX products require temperatures above +60 °C for curing. The heating time of the components must be added to the curing time. Heating can be done for example in air convection ovens, with IR radiators or using inductive systems.

Surface pretreatment

To achieve optimum bond strength, the surfaces must be free from dust, oil, grease, separating agents and other contaminations. For cleaning, we recommend using cleaners from the DELOTHEN series.

After cleaning, the adhesion of the adhesive can be further enhanced by sand blasting, grinding or pickling the surface.

Storage life

After delivery, in the unopened original container: see Technical Data Sheet of the product.

Use

DELO MONOPOX products are used for high-strength bonding of components which are extremely stressed to some extent. These products are constructional elements. The adhesive selection is supposed to be optimized regarding component material, stresses, construction and processing technology. Application areas are mainly found in automotive and automotive supplier industry, mechanical and electrical engineering, electronics, plant construction, construction technology, energy and environmental technology.

Further information

More type-specific properties are included in the Technical Data Sheets, Material Safety Data Sheets and Instructions for Use. For application tests and any question you might have regarding the use of DELO products, please do not hesitate to contact our Engineering Department.

Application examples

▪ High-strength bonding, alternative to soldering

For example bonding of carbide or steel, structural bonding in vehicle and steel construction

- DELO MONOPOX 1197
- DELO MONOPOX AD286
- DELO MONOPOX AD295

▪ Use at high temperatures

- DELO MONOPOX HT281
- DELO MONOPOX HT282

▪ High run resistance

- DELO MONOPOX 1197

▪ Casting of electronic components

- DELO MONOPOX 6093
- DELO MONOPOX 6095
- low chloride ion content, improved corrosion properties

▪ Fast curing

- DELO MONOPOX AD066
- DELO MONOPOX SJ2720

▪ Low-temperature curing

- DELO MONOPOX LT204
- DELO MONOPOX LT2224

CONTACT

DELO Industrial Adhesives
Headquarters

▶ **Germany** · Windach / Munich

- ▶ **China** · Shanghai
- ▶ **Japan** · Yokohama
- ▶ **Malaysia** · Kuala Lumpur
- ▶ **Singapore**
- ▶ **South Korea** · Seoul
- ▶ **Taiwan** · Taipei
- ▶ **Thailand** · Bangkok
- ▶ **USA** · Sudbury, MA

www.DELO-adhesives.com

Our selection charts/material selection guides are a technical selection aid giving an overview of various product variants. We will be pleased to provide you with sales details, such as available container sizes, stock availability and minimum order quantities, on request. The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e.g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

© DELO – This brochure including any and all parts is protected by copyright. Any use not expressly permitted by the Urheberrechtsgesetz (German Copyright Act) shall require DELO's written consent. This shall apply without limitation to reproductions, duplications, disseminations, adaptations, translations and microfilms as well as to the recording, processing, duplication and/or dissemination by electronic means. 07/17

ADHESIVES

DISPENSING

CURING

CONSULTING

DELO

DELO



SELECTION CHART

DELO MONOPOX
Aminic

Epoxy resins
one-component · heat-curing · tough-hard