

# DELO

## Instructions for Use & General Information on the Product Group

### DELO®-ML

Anaerobic adhesives



### Application areas

DELO®-ML are liquid, one-component adhesives that cure by exclusion of oxygen and under influence of metal ions. They are especially suitable for bonding metal components.

The dualbond types (DB) can additionally be cured with UV light or visible light.

The flexible, tension-equalizing DB types are also suitable for metal-to-glass or certain metal-to-plastic bondings.

All DELO®-ML adhesives can be cured faster by increasing the temperature or by using activators. The DB types can be fixed quickly within seconds by exposing them to UV light.

### **Application possibilities:**

- Form-closed connecting of axisymmetric components → Fixing
- Securing of screws → Screw securing
- Sealing of pipe, screw and flange connections → Surface or thread sealing
- Dual-curing DELO®-ML types (DB) can also be used for small casting applications as well as certain glass and plastic bondings.

### **The disparate ML types**

- can easily be distinguished from each other thanks to their disparate colors:
- Low-strength (yellow)
- Medium-strength (blue)
- High-strength (green)
- Dual-curing: Anaerobic and UV- or light-curing (yellowish transparent)

## **Preparation of the components to be bonded**

The contact surfaces must be free of oil, grease and other contaminations in order to achieve optimal bond strength. We provide our DELOTHEN cleaners. You can find more details in the “DELOTHEN Cleaners” technical information.

After cleaning, adhesion to the component can be further improved by surface pretreatment. You can find further information in the written information on surface pretreatment.

The suitability and strength of the adhesive are to be verified on original components under application-specific conditions. After customer-specific tests, DELO®-ML 5327 can also be used on slightly oily surfaces.

## **Preparation of the adhesive**

The adhesives are usually supplied ready for use. In case of cool storage, the containers must be conditioned to room temperature (+18 to +25 °C) before use to prevent condensation during adhesive application. Head addition is not permitted. The conditioning time of containers up to 50 ml is approx. 0.5 h. The conditioning time of containers up to 1,000 ml is approx. 4 h. You can find detailed, product-specific information on adhesive preparation in the specific Technical Data Sheet.

## Processing

The products are supplied ready for use. Depending on the scope of delivery, they can be processed manually directly from the container or by means of DELO® dispensing units (such as pinch valve).

Dispensing valves and material-conveying parts must be thoroughly cleaned before using the adhesive. Residues of other products must be removed without leaving any residues.

PE, HDPE, PP and PTFE, which are sufficiently resistant to chemicals and are completely opaque when using the dual-curing DELO®-ML products, are suitable as materials for material-conveying parts, such as dispensing valves and product tubes. When using other materials, the materials must be checked for suitability and compatibility. It is not recommended to use PU or metal. This is how unintentional curing in the system can be prevented. In addition, it must be kept in mind that anaerobic products may also cure in the system during production downtimes (exclusion of oxygen).

The adhesive is often applied to only one component to be bonded. However, it is also possible to apply the adhesive to both components.

It must be ensured that the complete gap is completely filled with DELO®-ML over the entire bonding surface. This is how trapped air, which can prevent complete curing, is avoided. For securing screws and for sealings, the adhesive is to be applied onto all turns of the thread which are in mesh after assembly.

For blind holes, enough adhesive must be dispensed to the bottom of the borehole so that air in the borehole can escape. During assembly, the adhesive spreads inside the complete gap as a consequence of the radial and axial movement of the screw or the bolt. When applying an adhesive bead for subsequent spreading through the joining pressure, an “open” bead must be ensured. That is to say that the bead must be dispensed in such a way that the adhesive presses the air outwards, and the air is not trapped. When sealing surfaces, the use of a short-haired roller has proven to be efficient. The roller must be soaked completely in order to prevent trapped air.

You can find further detailed, product-specific information on the processing of each product in the specific Technical Data Sheet.

## Activators

DELO®-QUICK is used to accelerate curing of DELO®-ML on metal and passive metal surfaces (zinc-plated, chrome-plated, cadmium-plated, etc.), as well as for curing on certain plastic types.

1. Apply DELO®-QUICK to one surface.
2. Let it evaporate.
3. Apply DELO®-ML to the other surface.
4. Join the components.

Curing can also be accelerated by brushing the components with a brass or copper brush.

## Curing

Curing proceeds by exclusion of oxygen and under the catalytic effects of metal ions. It can be accelerated through heat and/or DELO®-QUICK for DELO®-ML. Dual-curing products can be cured anaerobically or by light of the suitable wavelength and intensity. You can find the detailed, product-specific information on the processing of each product in the specific Technical Data Sheet.

## Instructions and advice for occupational health and safety

See Material Safety Data Sheet

## Storage

In unopened original container. Cool storage is recommendable.

Storage life: see Technical Data Sheet

# CONTACT

**DELO** Industrial Adhesives

- ▶ **USA** · Sudbury, MA · Phone +1 978 254 5275 · [usa@DELO-adhesives.com](mailto:usa@DELO-adhesives.com) · [www.DELO-adhesives.com/us](http://www.DELO-adhesives.com/us)
- ▶ **Germany** · Windach/Munich (Headquarters) · Phone +49 8193 9900-0 · [info@DELO.de](mailto:info@DELO.de) · [www.DELO.de](http://www.DELO.de)
- ▶ **China** · Shanghai · Phone +86 21 2898 6569 · [china@DELO-adhesives.com](mailto:china@DELO-adhesives.com) · [www.DELO-adhesives.com/cn](http://www.DELO-adhesives.com/cn)
- ▶ **Malaysia** · Kuala Lumpur · Phone +65 6807 0800 · [malaysia@DELO-adhesives.com](mailto:malaysia@DELO-adhesives.com) · [www.DELO-adhesives.com/en](http://www.DELO-adhesives.com/en)
- ▶ **Singapore** · Phone +65 6807 0800 · [singapore@DELO-adhesives.com](mailto:singapore@DELO-adhesives.com) · [www.DELO-adhesives.com/en](http://www.DELO-adhesives.com/en)
- ▶ **South Korea** · Seoul · Phone +82 31 450 3038 · [korea@DELO-adhesives.com](mailto:korea@DELO-adhesives.com) · [www.DELO-adhesives.com/en](http://www.DELO-adhesives.com/en)
- ▶ **Taiwan** · Taipei · Phone +886 2 6639 8248 · [taiwan@DELO-adhesives.com](mailto:taiwan@DELO-adhesives.com) · [www.DELO-adhesives.com/cn](http://www.DELO-adhesives.com/cn)

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

© DELO® – This document including any and all parts is protected by copyright. Any use not expressly permitted by the Urheberrechtsgesetz (German Copyright Act) shall require DELO®'s written consent. This shall apply without limitation to reproductions, duplications, disseminations, adaptations, translations and microfilms as well as to the recording, processing, duplication and/or dissemination by electronic means.

03/17