

DELO

Instructions for Use &
General Information
on the Product Group

DELO® MONOPOX Aminic

One-component adhesives
and casting resins



Application areas

DELO® MONOPOX products are one-component, heat-curing products. They are predominantly used as adhesives and casting compounds in electronics, electrical engineering, mechanical engineering and tool construction.

Processing

Preparation/pretreatment → Application → Joining → Heat curing

Preparation of the components to be bonded

The contact surfaces must be free of oil, grease and other contaminations in order to achieve optimal bond strength. We provide our DELOTHEN cleaners. You can find more details about “DELOTHEN Cleaners” on the DELOTHEN Technical Data Sheet.

After cleaning, adhesion to the component can be further improved by surface pretreatment. You can find further information on surface pretreatment section.

The suitability and strength of the adhesive are to be verified on original components under application-specific conditions.

Processing of the adhesive

The products are supplied ready for use. Depending on the scope of delivery, they can be processed manually directly from the container or by means of devices such as DELOMAT dispensing units.

The adhesive must be conditioned to room temperature for the appropriate amount of time before bonding without heat addition in the supplied original container (see Technical Data Sheet).

Condensation water on the adhesive and the substrate must be prevented.

Freezing and thawing the adhesive again is not permitted!

When applying DELO® MONOPOX to larger areas, DELO recommends using a scraper or a notched trowel to achieve good wetting of the components to be bonded.

Euro cartridges:

1. Cut the Euro cartridge tip.
2. Screw on the dispensing tip.
3. Insert the Euro cartridge into the dispensing gun.

DELOMAT with Euro cartridge retainer:

1. Insert the cartridge into the cartridge pipe.
2. Tightly screw the swivel nut of the pressure tank cover onto the cartridge pipe.
3. If necessary, put the cartridge pipe with the cartridge through the retaining bent.
4. Cut the cartridge tip at its upper end.
5. Carefully screw the cartridge into the thread of the valve or attach the adapter for the flexible discharge site. Caution! Make sure that the o-ring is inserted correctly!

Hobbock:

1. Remove the cover.
2. Insert the follower plate.

Remember that the storage life depends on the ambient temperature! Please contact our experts if you have any questions!

**CAUTION!****An exothermic reaction during preheating is possible!**

Maximum preheating temperature: +86 °F. Higher preheating temperatures depend on the product and are sometimes feasible.

Curing

The curing temperatures and times are product-specific and can be found in the appropriate Technical Data Sheet. The heating time of the components must be added to the curing time.

Heat curing can be achieved in air convection ovens, with IR transmitters, or with other suitable heat sources, such as thermodes or induction systems. It is important that the adhesive, and not the joining parts, reach the specified curing temperature. Otherwise the adhesive will not be fully cured.

If the temperatures used for curing are below the temperature ranges specified in the Technical Data Sheet, curing is decelerated, or the product cures incompletely or not at all. The adhesive must not be heated beyond the maximum curing temperature specified in the Technical Data Sheet.

When bonding large areas, tensions during the heating, curing and cooling phases (for example by tempering) must be avoided.

You can find the detailed, product-specific information on the processing of each product in the specific Technical Data Sheet.

Cleaning

Isopropanol and acetone are generally suitable cleaners for aminic DELO® MONOPOX adhesives.

The type of cleaner to be used depends on the specifications of the dispensing device manufacturer. The manufacturer's instructions must be followed in any case.

Details about cleaning of valves and systems can be found in the cleaning instructions for aminic DELO® MONOPOX products.

Instructions and advice for occupational health and safety

See Material Safety Data Sheet

Storage

After delivery, remove the package from the transport packaging and condition to the storage temperature in unopened condition for at least 4 h (see figure).

Please make sure that frozen container is only minimally touched as large temperature difference between container and adhesive may lead to the adhesive becoming "detached" from the inner cartridge wall. It is recommended that the container is removed at its rear end or thermally insulating gloves are used.




Storage life and storage temperature can be drawn from the Technical Data Sheet
 The product may be stored in the unopened original container only.
 The storage temperature specified in the Technical Data Sheet must not be undershot.

Innen/Inside

DELO

Instructions for cooled package (0°C – +10°C)
 How to handle cooled DELO adhesives after arrival

冷置包装使用说明 (0°C – +10°C)
 怎样处理冷置包装的 DELO 胶水




<p>1 Unpacking Unpack the adhesive</p> <p>1 打开外包装 取出装有胶水的纸桶</p> 	<p>2 Storage Store in a fridge at 0°C to +10°C for at least 4 hours prior to step 3</p> <p>2 储存 进入第三步前，请在 0 – +10°C 冷藏室中至少储存 4 小时</p> 	<p>3 Conditioning Allow the adhesive to adjust to room temperature prior to use</p> <p>3 回温 使用前，请将胶水的温度恢复至室温 (+23°C)</p> 
---	---	--

Innen/Inside

DELO

Instructions for frozen package (-18°C)
 How to handle frozen DELO adhesives after arrival

冷冻包装操作指南 (-18°C)
 怎样处理冷冻包装的 DELO 胶水

<p>1 Unpacking Unpack the adhesive</p> <p>1 打开外包装 取出装有胶水的纸桶</p> 	<p>2 Storage Store in a freezer at -18°C in unopened box for at least 4 hours prior to step 3</p> <p>2 储存 进入第三步前，请将纸桶密封不动在 -18°C 冷冻室中至少储存 4 小时</p> 	<p>3 Conditioning Allow the adhesive to adjust to room temperature prior to use</p> <p>3 回温 使用前，请将胶水的温度恢复至室温 (+23°C)</p> 
---	--	--

Handling of cooled package
 +32 °F – +50 °F (0 °C – +10 °C) storage

Handling of dry ice package
 –0,4 °F (-18 °C) storage

CONTACT

DELO Industrial Adhesives

- ▶ **USA** · Sudbury, MA · Phone +1 978 254 5275 · usa@DELO-adhesives.com · www.DELO-adhesives.com/us
- ▶ **Germany** · Windach/Munich (Headquarters) · Phone +49 8193 9900-0 · info@DELO.de · www.DELO.de
- ▶ **China** · Shanghai · Phone +86 21 2898 6569 · china@DELO-adhesives.com · www.DELO-adhesives.com/cn
- ▶ **Malaysia** · Kuala Lumpur · Phone +65 6807 0800 · malaysia@DELO-adhesives.com · www.DELO-adhesives.com/en
- ▶ **Singapore** · Phone +65 6807 0800 · singapore@DELO-adhesives.com · www.DELO-adhesives.com/en
- ▶ **South Korea** · Seoul · Phone +82 31 450 3038 · korea@DELO-adhesives.com · www.DELO-adhesives.com/en
- ▶ **Taiwan** · Taipei · Phone +886 2 6639 8248 · taiwan@DELO-adhesives.com · www.DELO-adhesives.com/cn

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

© DELO® – This document including any and all parts is protected by copyright. Any use not expressly permitted by the Urheberrechtsgesetz (German Copyright Act) shall require DELO®'s written consent. This shall apply without limitation to reproductions, duplications, disseminations, adaptations, translations and microfilms as well as to the recording, processing, duplication and/or dissemination by electronic means.

07/17

Adhesives

Dispensing

Curing

Consulting

DELO