

# DELO DUALBOND® photoinitiated-curing acrylates

		UV- /light- / heat-curing		UV- /light- / humidity-curing					
Product code		AD465	GE4707	GE4910	GE4919	GE4949	MF4992	AD4930	AD4950
Application area	B=bonding, S=sealing	B/S	S	B/S	B	B	B	B	B
Color of cured product	in 0.004 in (0.1 mm) layer thickness	red fluorescent	blue fluorescent	colorless clear	yellowish	anthracite gray	red fluorescent	yellowish	colorless
	in 0.04 in (1.0 mm) layer thickness	–	blue fluorescent	–	yellowish slightly milky	black	–	–	–
Viscosity [cP = mPas] at +73 °F (+23 °C)	rheometer; SR = shear rate	6,500 SR 10/s	1,500 SR 2/s	2,300 SR 2/s	11,000 SR 2/s	–	100,000 SR 2/s	14,000 SR 2/s	25,400 SR 2/s
	Brookfield, DIN EN 12092	24,000	1,500	2,000	–	35,000	215,000	–	36,000
Wavelength range for curing [nm]		320 – 420	← 320 – 450 →						
Recommended irradiation time [s] LED 400 nm, LED intensity 200 mW/cm <sup>2</sup>		2	7	4	4	10	13	3	4
Curing time until final strength		5 min @ +230 °F (+110 °C) 3 min @ +266 °F (+130 °C)	50 min @ +248 °F (+120 °C) 25 min @ +266 °F (+130 °C)	–	–	–	–	–	–
Compression shear strength DELO® Standard 5	glass / glass	3,335 psi <sup>1)</sup> (23 MPa)	–	1,015 psi <sup>1)</sup> (7 MPa)	2,175 psi <sup>3)</sup> (15 MPa)	1,450 psi <sup>3)</sup> (10 MPa)	1,305 psi <sup>4)</sup> (9 MPa)	1,305 psi <sup>1)</sup> (9 MPa)	1,305 psi <sup>1)</sup> (9 MPa)
	glass / Al	3,190 psi <sup>1)</sup> (22 MPa)	–	870 psi <sup>1)</sup> (6 MPa)	2,900 psi <sup>3)</sup> (20 MPa)	1,015 psi <sup>4)</sup> (7 MPa)	1,160 psi <sup>4)</sup> (8 MPa)	580 psi <sup>1)</sup> (4 MPa)	870 psi <sup>1)</sup> (6 MPa)
	glass / stainless steel	2,755 psi <sup>1)</sup> (19 MPa)	580 psi <sup>2)</sup> (4 MPa)	–	–	–	870 psi <sup>4)</sup> (6 MPa)	–	–
	glass / PA	2,030 psi <sup>1)</sup> (14 MPa)	725 psi <sup>2)</sup> (5 MPa)	870 psi <sup>1)</sup> (6 MPa)	1,450 psi <sup>3)</sup> (10 MPa)	1,450 psi <sup>3)</sup> (10 MPa)	1,160 psi <sup>4)</sup> (8 MPa)	1,160 psi <sup>1)</sup> (8 MPa)	1,160 psi <sup>1)</sup> (8 MPa)
	glass / PBT	725 psi <sup>1)</sup> (5 MPa)	–	290 psi <sup>1)</sup> (2 MPa)	–	580 psi <sup>3)</sup> (4 MPa)	580 psi <sup>4)</sup> (4 MPa)	580 psi <sup>1)</sup> (4 MPa)	580 psi <sup>1)</sup> (4 MPa)
	glass / FR4	3,045 psi <sup>1)</sup> (21 MPa)	–	1,305 psi <sup>1)</sup> (9 MPa)	–	–	1,305 psi <sup>4)</sup> (9 MPa)	1,305 psi <sup>1)</sup> (9 MPa)	1,595 psi <sup>1)</sup> (11 MPa)
	PC / PC	–	725 psi <sup>2)</sup> (5 MPa)	–	2,900 psi <sup>3)</sup> (20 MPa)	1,015 psi <sup>4)</sup> (7 MPa)	1,160 psi <sup>4)</sup> (8 MPa)	–	–
	PMMA / PMMA	–	–	–	–	–	–	1,015 psi <sup>1)</sup> (7 MPa)	1,160 psi <sup>1)</sup> (8 MPa)
Tensile strength	by the criteria of DIN EN ISO 527	2,465 psi (17 MPa)	725 psi (5 MPa)	870 psi (6 MPa)	2,175 psi (15 MPa)	–	1,160 psi (8 MPa)	725 psi (5 MPa)	1,160 psi (8 MPa)
Elongation at tear [%]	by the criteria of DIN EN ISO 527	220	460	315	110	–	350	45	270
Young's modulus		46.4 ksi (320 MPa) DIN EN ISO 527	–	2,465 psi (17 MPa) DIN EN ISO 527	–	17.1 ksi (118 MPa) DMTA	< 14.5 ksi (100 MPa) DIN EN ISO 527	4,350 psi (30 MPa) DIN EN ISO 527	6,525 psi (45 MPa) DIN EN ISO 527
Shore hardness	by the criteria of DIN EN ISO 868	D 50	A 36	A 62	D 40	A 85	A 58	A 80	A 77
Glass transition temperature T <sub>g</sub>		+212 °F (+100 °C) rheometer	–	+75 °F (+24 °C) rheometer	+230 °F (+110 °C) DMTA	–	+150 °F (+66 °C) DMTA	+176 °F (+80 °C) DMTA	+161 °F (+72 °C) DMTA
Average coefficient of linear expansion [ppm / K] in the temperature range	TMA	–	–	235 (+86 °C to +284 °C) (+30 °C to +140 °C)	–	–	–	210 (+86 °C to +284 °C) (+30 °C to +140 °C)	217 (+86 °C to +284 °C) (+30 °C to +140 °C)
Shrinkage [vol. %]	DELO® Standard 13	5.6	6.5	5.4	7	4.6	4.3	3	4.6
Water absorption [weight %]	by the criteria of DIN EN ISO 62 24 h at +73 °F (+23 °C)	1.2	0.8	1.3	3	5.8	2.8	0.6	2.5
Special features of product		dry surface very fast curing very good plastic/ metal adhesion	good flow behavior well suitable for sealing applications high temperature resistance	well suitable for potting, encapsulation and sealing applications flexible high temperature resistance	multi-purpose adhesive dry surface	multi-purpose adhesive opaque good plastic adhesion	multi-purpose adhesive high temperature resistance good plastic/ metal adhesion flexible	multi-purpose adhesive good corrosion resistance good shadow strength 2 – 3 MPa	multi-purpose adhesive good plastic adhesion

Compression shear strength – irradiation and curing conditions:

- <sup>1)</sup> UVA intensity 55 – 60 mW/cm<sup>2</sup>, 60 s      <sup>3)</sup> LED 400 nm, LED intensity 200 mW/cm<sup>2</sup>, 30 s  
<sup>2)</sup> LED 400 nm, LED intensity 200 mW/cm<sup>2</sup>, 60 s      <sup>4)</sup> LED 400 nm, LED intensity 60 mW/cm<sup>2</sup>, 60 s

**AD** = Adhesive    **GE** = General Encapsulant    **MF** = Multi Function

## Product description

DELO DUALBOND® are one-component, solvent-free acrylate-based adhesives.

## Usual temperature range

DELO DUALBOND® acrylates are normally used in a temperature range of –40 °F to +248 °F (–40 °C to +120 °C) (or +302 °F [+150 °C]), see special features of product “high temperature resistance”). Many product properties depend on the temperature and can change permanently, in particular at high temperatures. Therefore, it has to be checked before each use whether a certain adhesive is suitable for the temperatures in the required area of application. Please see the Technical Data Sheet for more information on how our products react to temperatures.

## Processing

The products are normally delivered ready for use. They are processed directly from the container or using dispensing units.

## Curing

Primary curing of the UV-/light- and humidity-curing acrylates DELO DUALBOND® can only be achieved if the complete adhesive is reached by light of the suitable wavelength and sufficient intensity for the required period of time. Adhesive in shadowed areas crosslinks through a second curing mechanism. This that no adhesive remains liquid in shadowed areas. Secondary curing proceeds through a reaction with air humidity or the remaining humidity on the components to be bonded. The curing speed is approx. 0.08 in (2 mm) / 24 h at 50 % rel. humidity and +73 °F (+23 °C). Primary curing by light is absolutely necessary for a professional bonding as curing by humidity does not show any considerable strength build-up. UV-/light- and heat-curing DELO DUALBOND® products can be cured by both heat and light. Complete curing by light can only proceed if the total adhesive is reached by light of the suitable wavelength. Adhesive not reached by light can be completely cured by subsequent heat input. Irradiation times, curing temperatures and times are product-specific and can be found in the appropriate Technical Data Sheet.

## Surface pretreatment

For optimal bond strength, the surfaces to be bonded must be free of dust, oil, grease, separating agents and other contaminations. After cleaning, adhesion can be further improved by surface sand blasting, flaming, plasma treatment or corona treatment.

## Preservability

After delivery, most DELO DUALBOND® products are preservable for 6 months if stored in the unopened original container at room temperature. You can find detailed information in the Technical Data Sheet of the product.

## Use

It is the user's responsibility to test the suitability and strength of the adhesive on original components for the intended purpose by considering all specific requirements. DELO DUALBOND® products are predominantly used in electronics, microelectronics, electrical engineering, optics and precision engineering for bonding, coating, fixing and sealing.

## Notes

More type-specific properties are included in the Technical Data Sheets, Material Safety Data Sheets and Instructions for Use. For application tests and any question you might have regarding the use of DELO® products, please do not hesitate to contact the DELO® Engineering. Please also refer to the DELO® PHOTOBOND® and DELO® KATIOBOND® Selection Charts. DELO® PHOTOBOND® are also photoinitiated, one-component and solvent-free, acrylate-based adhesives. They can be cured very quickly until final strength by irradiation with UV light or visible light (VIS). DELO® KATIOBOND® are photoinitiated, one-component and solvent-free adhesives based on cationic-polymerizing epoxy resins. The adhesives cure until final strength after a minimum irradiation time even after irradiation is stopped. As a result, the light-activated types offer the possibility of preactivation. With this procedure two opaque components can be bonded. UV-curing DELO® KATIOBOND® can be used as Dam&Fill products for chip encapsulation. All DELO® KATIOBOND® products have a completely dry surface after curing.

### Curing of photoinitiated adhesives

Curing with UV light or visible light in the respective wavelength range. DELOLUX® LED curing lamps are especially suitable as per the chart below. All standard DELOLUX® HID discharge lamps are also suitable.

Lamp type	DELOLUX® 80, DELOLUX® 50 and 502, DELOLUX® 20 and 202		
	365	400	460
DELO DUALBOND® AD465	+	++	-
DELO DUALBOND® GE4707	+	++	-
DELO DUALBOND® GE4910	+	++	-
DELO DUALBOND® GE4919	+	++	-
DELO DUALBOND® GE4949	+	++	-
DELO DUALBOND® MF4992	+	++	-
DELO DUALBOND® AD4930	+	++	-
DELO DUALBOND® AD4950	+	++	-

++ particularly suitable + suitable - not suitable

### Product selection

Application area	Potting / encapsulation Coating	Bonding of UVA- and VIS-permeable materials	Bonding of VIS-permeable materials	Bonding of opaque materials	Bonding, potting, encapsulation, coating with reliable curing in shadowed areas
Products	DELO® KATIOBOND®, DELO® PHOTOBOND®	DELO® KATIOBOND®, DELO® PHOTOBOND®	Light-activated DELO® KATIOBOND®, light-curing DELO® PHOTOBOND®	Light-activated DELO® KATIOBOND®, light-activated humidity-curing DELO® PHOTOBOND® LA	DELO DUALBOND®
Processing suggestion	Application ↓ Irradiation	Application ↓ Joining ↓ Irradiation	Application ↓ Preactivation ↓ Joining	Application ↓ Joining	Application ↓ Joining ↓ Irradiation and/or heat or air humidity

## CONTACT

**DELO** Industrial Adhesives  
Headquarters

► **Germany** · Windach / Munich

- **China** · Shanghai
- **Japan** · Yokohama
- **Malaysia** · Kuala Lumpur
- **Singapore**
- **South Korea** · Seoul
- **Taiwan** · Taipei
- **Thailand** · Bangkok
- **USA** · Sudbury, MA

www.DELO-adhesives.com

Our selection charts / material selection guides are a technical selection aid giving an overview of various product variants. We will be pleased to provide you with sales details, such as available container sizes, stock availability and minimum order quantities, on request. The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e.g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. All products provided by DELO® are subject to DELO®'s General Terms of Business. Verbal ancillary agreements are deemed not to exist.

© DELO® – This brochure including any and all parts is protected by copyright. Any use not expressly permitted by the Urheberrechtsgesetz (German Copyright Act) shall require DELO®'s written consent. This shall apply without limitation to reproductions, duplications, disseminations, adaptations, translations and microfilms as well as to the recording, processing, duplication and / or dissemination by electronic means.

01/19

ADHESIVES

DISPENSING

CURING

CONSULTING

**DELO**

**DELO**



## SELECTION CHART

**DELO DUALBOND®**

Acrylates  
one-component ·  
UV-/light-/heat-curing · UV-/light-/humidity-curing